

Gel-Al-cadmium

(Kpau Gel Al O<sub>3</sub>)

VII 6684

1965

Ni-Zn, Gd<sub>3</sub>AlF<sub>4</sub>O<sub>12</sub> (Tr)

Foiles C.L., Tomizuke C.T.,

J. Appl. Phys., 1965, 36, 3839-3842

T

$\text{GdCl}_3 \cdot \text{AlCl}_3$       мокозов и. с.      1974  
                                4 гр.

"Н. ксопр. хххххххх", 1974,  
(Tm)      22(4), 1938-42.

● (ав.  $\text{NdCl}_3 \cdot \text{AlCl}_3$ )  
T

*GdAl<sub>3</sub>Cl<sub>12</sub>*      *отмск 9089*      1979  
*GdFe<sub>3</sub>Cl<sub>12</sub>*

11 В60. Газообразные комплексы хлорида гадолиния с хлоридами алюминия и железа. Cosandey M., Emtepegeger F. P. Gaseous complexes of gadolinium chloride with aluminum and iron chlorides. «J. Electrochem. Soc.», 1979, 126, № 9, 1601—1603 (англ.)

Методами переноса, закалки равновесий, хим. транспорта изучено равновесие в системе  $\text{GdCl}_3(\text{тв.}) - \text{M}_2\text{Cl}_6(\text{г.})$ , где  $\text{M} = \text{Al}$  (I),  $\text{Fe}$  (II). Для полученных в газ. фазе комплексов  $\text{GdM}_3\text{Cl}_{12}$  (г) определены термодинамич. константы:  $\Delta H = 34$  кДж/моль и  $\Delta S = 10$  Дж/град·моль для I; для II  $\Delta H = 51 - 55$  кДж/моль,  $\Delta S \sim 10$  Дж/град·моль по данным хим. транспорта. При  $550^\circ$  и давл. 1 атм давл. паров  $\text{GdCl}_3$  (III)  $2 \cdot 10^{-2}$  атм, с II в этих же условиях давл. III  $2 \cdot 10^{-3}$  атм и соизмеримо с давл. чистого III при  $950^\circ$ . Отмечена более высокая устойчивость  $\text{GdAl}_3\text{Cl}_{12}$  (г) по сравнению с  $\text{GdFe}_3\text{Cl}_{12}$  (г), что согласуется с лит. данными. А. Т. Фалькенгоф

*4H, 4S*

*2.1980.111*

Commenc 9089 1979

GdAl<sub>3</sub>Cl<sub>12</sub>  
(g)

GdFe<sub>3</sub>Cl<sub>12</sub>  
(g)


(AH, AS)

Emmenegger

91: 199808b Gaseous complexes of gadolinium chloride with aluminum and iron chlorides. Cosandey, M.; Emmenegger, F. P. (Inst. Inorg. Chem., Univ. Fribourg, 1700 Fribourg, Switz.). *J. Electrochem. Soc.* 1979, 126(9), 1601-3 (Eng). In view of a possible application for the chem. vapor deposition of Gd<sub>3</sub>Fe<sub>5</sub>O<sub>12</sub>, the equil. GdCl<sub>3</sub>(s) + 1.5L<sub>2</sub>Cl<sub>6</sub>(g) = GdL<sub>3</sub>Cl<sub>12</sub>(g) (L = Al, Fe) was investigated by entrainment, quenching, and chem. transport expts. The results are for Al:  $\Delta H = 34 \text{ kJ/mol}$ ,  $\Delta S = 10 \text{ J/mol.K}$ . For Fe the results are:  $\Delta H \approx 53 \text{ kJ/mol}$ . At 550° and  $p_{\text{Al}_2\text{Cl}_{16}} = 1 \text{ atm}$  the apparent vapor pressure of GdCl<sub>3</sub> is  $2 \times 10^{-2} \text{ atm}$  and at  $p_{\text{Fe}_2\text{Cl}_{16}} = 1 \text{ atm}$  it is approx.  $2 \times 10^{-3} \text{ atm}$  as compared with  $1.3 \times 10^{-3} \text{ atm}$  at 950° for GdCl<sub>3</sub> alone. The higher stability of GdAl<sub>3</sub>Cl<sub>12</sub>(g) against GdFe<sub>3</sub>Cl<sub>12</sub>(g) corresponds to stability trends obsd. in other metal chloride gaseous complexes.

P.A.1979.0.124

1981



95: 71145y Crystallization of gadolinium aluminum orthoborate in a melt-solution of potassium trimolybdate. Timchenko, T. I.; Pashkova, A. V.; Azizov, A. V.; Troshin, A. Yu. (Mosk. Gos. Univ., Moscow, USSR). *Dokl. Akad. Nauk SSSR* 1981, 258(1), 106-9 [Crystallogr.] (Russ). The optimum crystn. conditions for  $\text{GdAl}_3(\text{BO}_3)_4$  from a  $\text{K}_2\text{Mo}_3\text{O}_{10}$  melt were studied. The compn. ranges for  $\text{Gd}_2\text{O}_3$ ,  $\text{Al}_2\text{O}_3$ , and  $\text{B}_2\text{O}_3$  were detd. The temp. dependence of the solv. of  $\text{GdAl}_3(\text{BO}_3)_4$  was measured. The heat of soln. is 12-14 kcal/mol.

DK foln

CA 1981, 95, n 8

$GdAl_3(BO_3)_4$

1983

Бедюковича Е. А.,  
Турчеко Т. У.

струм. Кристаллография,  
1983, 28, №, 1118-1123.

(см.  $YAl_3(BO_3)_4$ ; ?)

GdAl  
(enrich)

1983

99: 219795r Thermodynamic properties of alloys of gadolinium with low-melting metals. Kober, V. I.; Nichkov, I. F.; Raspopin, S. P.; Kuz'minykh, V. M. (USSR). *Splavy Redk. Met. Osobymi Fiz. Svoistvami: Redkozem. Blagorodn. Met.* 1983, 132-5 (Russ). Edited by Savitskii, E. M. Izd. Nauka: Moscow, USSR. Thermodn. properties were detd. from emf. measurements for binary alloys of Gd with Al, Ga, In (Group IIIA), Sn and Pb (Group IVA), Bi, Sb and Zn, at various temp. intervals between 638 and 1021K.

Meng CB-RK

⑦ A

GdGa, GdIn, GdSn, GdPb,  
GdBi, GdSb, GdZn

c.A.1983, 99, N26

$\text{GdCl}_3/\text{HgCl}_3$

1983

$\Delta_f H, P,$

$\Delta_f S;$

Steidle, G.; Breckmann,  
K. et al.

J. Phys. Chem. 1983,  
87(24), 6010-15.

(cces.  $\text{TmCl}_3/\text{HgCl}_3$ ; I).

$\text{CdF}_3$ -Al (DM. 28560)


1987

Зиекеев С.В., Петров А.А.

и др.)

сообщ.

Р; Уф. выш. Уф. институт, 1987, №, 126.

Нач - спектро  штрафное  
исследование  за неиспользование

Фториды юго-западные, нефелин, алюминиевые с полевым шпатом.

$\text{GdAl}_3(\text{BO}_3)_4$

1991

Ivanov S.N., Egorov G.V.

$(C_p, 6-300K)$  Fiz. Tverd. Tela (Leningrad)  
1991, 33(2), 626-7.

(c.u.   $\text{YAl}_3(\text{BO}_3)_4$ ;  $\bar{I}$ )

GdAlD<sub>3</sub>

1992

) 14 Б3095. Исследование магнитной фазовой диаграммы GdAlD<sub>3</sub> /Васюков В. Н., Галушко А. В., Кульбацкий В. П., Мелихов Ю. В., Телепа В. Т. //29-е Совещ. по физ. низ. температур, Казань, 30 июня — 4 июля, 1992: Тез. докл. Ч. 3.—Казань, 1992.—С. 56.—Рус.

Фазовая  
диаграмма

X. 1993, N 14